

Formulation Example

S 26-31 Liquid Highlighter Skinhancer

Ingredients

A

Ronastar® Golden Lights

Ronastar® Gold

Colorona® Gold Plus MP-25

RonaFlair® Balance Green

RonaFlair® Satin

B

Oxynex® ST Liquid

RonaCare® Bisabolol nat.
BELSIL EG 7

BELSIL REG 1102

Jolee 7245

Lipovol GTB

Isododecane

Eutanol G

Cosmol 222

Xiameter® PMX-200 Silicone Fluid 1.5CS

Belsil TMS 803

ABIL EM 90

Cetiol ININ

INCI US

[%]

(1)	ALUMINA (OR ALTERNATIVELY: SYNTHETIC SAPPHIRE) (AND) TITANIUM DIOXIDE (AND) TIN OXIDE	3.00
(1)	CALCIUM ALUMINUM BOROSILICATE (OR ALTERNATIVELY: CALCIUM SODIUM BOROSILICATE) (AND) TITANIUM DIOXIDE (AND) SILICA (AND) TIN OXIDE	2.40
(1)	MICA (AND) TITANIUM DIOXIDE (AND) IRON OXIDES	2.00
(1)	TITANIUM DIOXIDE (AND) MICA (AND) TIN OXIDE	3.00
(1)	ILLITE	2.00
(1)	DIETHYLHEXYL SYRINGYLIDENEMALONATE (AND) CAPRYLIC/CAPRIC TRIGLYCERIDE	0.50
(1)	BISABOLOL	0.20
(2)	DIMETHICONE (AND) DIMETHICONE/VINYL DIMETHICONE CROSSPOLYMER	26.00
(2)	DIMETHICONE (AND) DIMETHICONE/VINYLTRIMETHYLSILOXY-SILICATE CROSSPOLYMER	19.50
(3)	POLYGLYCERYL-3 DIISOSTEARATE	10.00
(4)	TRIBEHENIN	6.50
(5)	ISODODECANE	6.00
(6)	OCTYLDODECANOL	4.40
(7)	DIISOSTEARYL MALATE	4.00
(8)	DIMETHICONE	3.50
(2)	TRIMETHYLSILOXYSILICATE	3.00
(9)	CETYL PEG/PPG-10/1 DIMETHICONE	2.00
(6)	ISONONYL ISONONANOATE	2.00

Procedure:

Heat phase B to 60°C and stir until uniform. Add phase A and disperse until homogeneous. Fill into desired packaging.

Notes:


Appearance: Light yellow paste

Stability: 3 month @ RT, 1 month @ 50°C

Suppliers:

- (1) Merck KGaA, Darmstadt, Germany / EMD Performance Materials Corp.
- (3) Oleon GmbH oleon.com
- (5) China Chemical Reagent
- (7) Nisshin OilIO
- (9) Evonik Nutrition & Care GmbH

- (2) Wacker Chemie AG
- (4) Vantage Personal Care
- (6) BASF AG
- (8) Dow Chemical



Formulation Example

Products are warranted to meet the specifications set forth on their label/packaging and/or certificate of analysis at the time of shipment or for the expressly stated duration. EMD Performance Materials Corp. provides information and advice on application technologies and relevant regulations based upon its current knowledge and opinion. EMD PERFORMANCE MATERIALS CORP. MAKES NO REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE REGARDING OUR PRODUCTS, THEIR APPLICATION OR ANY INFORMATION PROVIDED IN CONNECTION THEREWITH. EMD Performance Materials Corp. shall not in any event be liable for incidental, consequential, indirect, exemplary or special damages of any kind resulting from any use or failure of the products. Customer is responsible for and must independently determine the suitability of our products for its intended use and processes. The foregoing information and suggestions are also provided without warranty of non-infringement as to intellectual property rights of third parties and shall not be construed as any inducement to infringe the rights of third parties. Customer shall be responsible for obtaining any applicable third party intellectual property licenses. All sales are subject to our complete Terms and Conditions of Sale. Prices are subject to change without notice. EMD Performance Materials Corp. reserves the right to discontinue products without prior notice.

© 2024 Merck KGaA, Darmstadt, Germany and/or its affiliates. EMD Electronics, the vibrant M, Colorona, Timiron, Xirona, RonaFlair, Ronastar, Ronaflux, Candurin, Eusolex, Parteck, OxyneX, RonaCare, IR3535, UV-Pearls, ASCIII, Luremin and Emblica are trademarks of Merck KGaA, Darmstadt, Germany or its affiliates. All other trademarks are the property of their respective owners. Detailed information on trademarks is available via publicly accessible resources.